

# Gelacryl™ TI

3-component poly-acrylate gel for tube injections

## Product Description

Gelacryl™ TI is a special 3-component poly-acrylate injection resin developed specifically for injection of preventative injection tubes. The viscosity does not increase momentarily as with other Gelacryl resins but builds up in linear fashion to allow optimal control of the re-injection process. Gelacryl TI has excellent adherence to the surface and has a post-expansion of up to 350% of the original volume in contact with water.

## Product Description

Gelacryl™ TI is a special 3-component poly-acrylate injection resin developed specifically for injection of preventative injection tubes. The viscosity does not increase momentarily as with other Gelacryl resins but builds up in linear fashion to allow optimal control of the re-injection process. Gelacryl TI has excellent adherence to the surface and has a post-expansion of up to 350% of the original volume in contact with water.

## Field of Application

Injection and re-injection of preventative injection tubes.

## Product Advantages

- Easy to use 3-component system
- Long gel time allows controlled injections
- Linear viscosity increase allows re-injection process to be monitored
- Post-expansion up to 350% in contact with water

## Technical Data / Properties

PROPERTY	VALUE
A1-component	
Viscosity (25 °C)	± 20 mPas
Density (20 °C)	1.12kg / dm <sup>3</sup>
Solids	42%
A2-component	
Viscosity (25 °C)	± 3 mPas
Density (20 °C)	± 0.95kg / dm <sup>3</sup>
Solids	100%

## Mix A1 + A2

Viscosity (25 °C)	± 18 mPas
Density (20 °C)	1.1 kg/dm <sup>3</sup>

## Application

### 1. Resin preparation

- Add the complete contents of Component A2 (small plastic bottle) to Component A1 (large plastic jerry can). Mix thoroughly.
- Prepare the B-component by filling a container with the same quantity of water as the mixed A-component (9.45 ltr). Add Component B1 to the water and mix for 3 minutes.
- The prepared components are pumped with a 1:1 ratio injection pump IP 2C-Gel.

### 2. Injection

- Connect the pump to the entrance port of the injection tube.
- Fill the tube with resin, when resin comes out of the exit port, this port is closed with a conical packer or wedge.
- Start injection by slightly increasing the pressure until the resin starts to flow.
- When the resin is expelled from the joint, stop the injection and allow the resin to react for 3–5 minutes.
- After waiting 3–5 minutes, the viscosity will have sufficiently increased to prevent flow of the material. The tube is now injected with fresh material to push the reacted material into the joint and fill all cavities.

### 3. Re-injection

- When re-injection is required, the tube needs to be flushed under low pressure with water. This needs to be done within the gel time of the resin.

### 4. Gel Times

GEL TIME	A-COMPONENT: A1 + A2 (L)	B-COMPONENT: WATER (L)	B1 (UNITS)
5'	9.45	9.45	2
10'	9.45	9.45	1

## Appearance

The mixed material cures into a flexible gel.

Component A1	Transparent liquid
Component A2	Transparent liquid
Component B1	White salt

## Packaging

Gelacryl TI A1	10kg blue plastic jerry can
Gelacryl TI	A2 0.5kg white plastic bottle
Gelacryl B1	25g plastic bottle

## Storage

Gelacryl TI A1, A2 and B1 should be stored in a frost free environment under cover, clear of the ground, in the original closed packaging.

Storage temperature must be below 35°C.

Shelf life: 1 year

## Consumption

Has to be estimated by the engineer or operator and depends on width and depth of the cracks and voids to be filled.

## Accessories

### To be ordered separately

- IP 2C-Gel air driven twin piston pump.
- Packers and connectors.

(Please consult the relevant data sheet).

## Health and Safety

Gelacryl TI Component A1 is classified as irritating.

Gelacryl TI Component A2 is classified as harmful.

Always wear appropriate protective gear: rubber gloves, goggles and boots. In case of contact with the eyes, flush with water for 15 minutes. If swallowed, call a physician immediately.

For full information, consult the relevant Material Safety Data Sheets.

[th.gcpat.com](http://th.gcpat.com) | Thailand customer service: 66 2 030 9700

Australia 1800 855 525 email: [au.sbmsales@gcpat.com](mailto:au.sbmsales@gcpat.com) New Zealand +64 9 448 1146 China Mainland +86 21 3158 2888 Hong Kong +852 2675 7898 India +91 124 488 5900 Indonesia +62 21 893 4260 Japan +81 3 5226 0231 Korea +82 32 820 0800 Malaysia +60 3 9074 6133 Philippines +63 49 549 7373 Singapore +65 6265 3033 Thailand +66 2 709 4470 Vietnam +84 8 3710 6168

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

Gelacryl is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2017 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140, USA

This document is only current as of the last updated date stated below and is valid only for use in Thailand. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on [www.th.gcpat.com](http://www.th.gcpat.com). Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2021-02-05

[th.gcpat.com/solutions/products/gelacryl-ti](http://th.gcpat.com/solutions/products/gelacryl-ti)